

Tensar TriAx® Stabilisation Geogrid Technical Data – TX160

This Tensar Technical Note provides parameters appropriate for the named Tensar TriAx geogrid for product identification purposes only. The parameters included relate to the stabilisation function of the Tensar TriAx product.


Model Specification documents are available from Tensar International. These include recommended clauses to assist Designers in the preparation of specification documents.

Technical Data

1. The primary geogrid function is stabilisation as defined by European Organisation for Technical Approvals (EOTA) Technical report TR41.
2. The geogrid has European Technical Approval (ETA) certification for the stabilisation of unbound layers by way of interlock with the aggregate.
3. The geogrid is manufactured in accordance with a management system which complies with the requirements of BS EN ISO 9001:2008.
4. The geogrid is a hexagonal structure with triangular apertures manufactured from a punched and stretched polypropylene sheet which is then oriented in three directions so that the resulting ribs of rectangular cross-

section have a high degree of molecular orientation which continues through the mass of the integral node.

5. The geogrid has a minimum of 2% finely divided carbon black content.
6. The properties contributing to the performance of a mechanically stabilised layer are:



Required certification for stabilisation function	European Technical Approval (ETA) Certificate		ETA 12/0530	
Performance related physical properties of the product	Product Characteristic	Unit	Declared Value	Tolerance
	Radial Secant Stiffness at 0.5% strain ¹	kN/m	390	-75
	Radial Secant Stiffness Ratio ¹	-	0.80	-0.15
	Junction Efficiency ²	%	100	-10
	Hexagon Pitch ³	mm	80	±4
Durability Statement ^{5,6,7}	The minimum working life of the geogrid in natural soils with a pH value between 4 and 9 is assumed to be 100 years in soil temperatures less than 15°C and expected to be 50 years in soil temperatures less than 25°C, when covered within 30 days.			
Properties for identification of the product	Radial Secant Stiffness at 2% strain ¹	kN/m	290	-65
	Hexagon Pitch ³	mm	80	±4
	Weight of the product ⁴	kg/m ²	0.220	-0.035

Tensor TriAx[®] Stabilisation Geogrid

Technical Data – TX160

Notes

1. Measured in accordance with EOTA Technical report TR41 B.1.
2. Measured in accordance with EOTA Technical report TR41 B.2.
3. Measured in accordance with EOTA Technical report TR41 B.4.
4. Measured in accordance with EOTA Technical report TR41 B.3.
5. Resistance to weathering of geogrid assessed in accordance with EN 12224. The retained strength is greater than 80% giving a maximum time for exposure after installation of 1 month.
6. Resistance to Oxidation is determined in accordance with EN ISO 13438. For the assumed working life of 50 years, the principle of Method A2 of EN ISO 12438 is followed, with the deviation that the exposure temperature is 120°C and the exposure time 28 days. Justification for this is provided in ETA Certificate 12/0530.
7. Resistance to acid and alkali liquids is determined in accordance with EN 14030.

Tensor

Tensor International Limited
Units 2-4 Cunningham Court
Shadsworth Business Park
Blackburn BB1 2QX
United Kingdom

Tel: +44 (0)1254 262431
Fax: +44 (0)1254 266867
e-mail: info@tensor.co.uk
tensor-international.com

The information in this document supersedes any and all prior Technical Notes for the product(s) designated above, is of an illustrative nature and supplied by Tensor International Limited free of charge for general information purposes only. Tensor reserves the right to amend product descriptions, properties and specifications at any time and without prior notice. This document does not form part of any contract or intended contract. Tensor International Limited excludes to the fullest extent lawfully permitted any and all liability whatsoever for any loss or damage howsoever arising out of the use of and reliance upon this information. It is your sole responsibility and you must assume all risk and liability for the final determination as to the suitability of any Tensor International Limited product and/or design for the use and in the manner contemplated by you in connection with a particular project.

Tensor and TriAx are registered trademarks.
Copyright © Tensor International Limited 2013.



Q 05288
ISO
9001:2008



EMS 86463
ISO
14001:2004



0799-CPD-110
ETA 12/0530
13